


TECHNICAL SHEET

PRODUCT: **ECONOSILIK**

Precipitated Silica (SiO₂)

Date: May/2012

Color	<u>WHITE</u>
Bulk Density (g/ml)	<u>0.12-0.16</u>
Tamped density (g/ml)	<u>0.17-0.21</u>
Maximum Loss on drying 105°C/ 2hrs (%)	<u>10</u>
pH value 5 %	<u>6.5-7.5</u>
Linseed oil absorption (dry basis) (ml/100 g)	<u>150-180</u>
BET surface area (m ² /g)	<u>150-200</u>



CONTROL DE CALIDAD

CINTHIA MORALES SALAZAR